

15550 KANEPOX MASTICOAT

PRODUCT DESCRIPTION

15550 KANEPOX MASTICOAT is an epoxy-polyamine based, two component, zinc phosphate containing, high built, self priming mastic coating with low volatile organic content (VOC). It is specially designed as a surface tolerant coating with excellent adhesion on marginally prepared steel surfaces and a wide range of existing coatings. Applied coating could dry down to 0°C. It is most often used in those applications where high film thickness in one coat is required. Can be applied to galvanized and all other metal surfaces.

RECOMMENDED USE

It has been developed as a surface tolerant protective coating for multi-purpose use such as water jet cleaned / wet blasted new or coated surfaces, blasted, mechanically cleaned or non-blasted surfaces. It can also be applied to damp surfaces. In cases where UV resistance is not necessary, it can be applied in the following areas as a high build primer or midcoat in anticorrosive paint systems;

- Oil refineries and petrochemicals,
- Chemical industry facilities,
- Structural steels,
- Bridges, dams, ports and docks
- Storage tanks and pipes exterior
- Underwater surfaces and ballast tanks of ships,

It can be applied as a primer and midcoat in paint systems where Im1 to Im4 immersion categories and C2 to C5, also CX corrosion categories are required according to ISO 12944-5 and ISO 12944-9 Standarts.

Complies with the requirements of LEED V4 – Low Emission Substances (substances with a maximum VOC content of 250 g/l)

PRODUCT CHARACTERISTICS

Finish: Semi-Matt	Density (g/ml) 1,50±0,10
Colour: Grey, Oxide Red, Beige	Spreading Rate (m²/l) 8,40 (100 microns DFT)
Thinner: Kanat Thinner 0625 (High Temp.) Kanat Thinner 0620 (Low Temp.)	Flash Point 43°C
Mixing Ratio (by volume) 16 Parts A Comp. + 4 Parts B Comp.	VOC (Volatile Organic Content) 132 g/l
Mixed Product; Volume Solids (%) 84±2	Application Methods Airless Spray, Roller
	Pot Life (20°C) 1,5 hours

DRYING SCHEDULE(*)

(100 microns/4 mils film thickness)

	Dry to Touch	Hard Dry	Dry to Over Coat Minimum
0°C	18 hours	36 hours	18 hours
5°C	12 hours	24 hours	12 hours
15°C	5 hours	7 hours	5 hours
25°C	3 hours	4 hours	3 hours
35°C	2,5 hour	3 hour	2,5 hour

Drying values are valid for defined dry film thickness and below 85% relative humidity.

Fully Cured: 7 days (20°C)

(*) Drying time depends on temperature, humidity and film thickness.

PACKAGING

One kit of **15550 KANEPOX MASTICOAT** is 20 l.

One pail of **15550 KANEPOX MASTICOAT** component A is 16 l.

One can of **KANEPOX HARDENER 0363** component B is 4 l.

SHELF LIFE

Part A–12 months, Part B–12 months when the material is stored in a cool and dry place in unopened original containers.

HEALTH/SAFETY PRECAUTIONS

Refer to the MSDS sheet prepared according to EU directives before use.

15550 KANEPOX MASTICOAT

SURFACE PREPARATION

Surfaces must be dry, clean, free of oil, grease and other foreign material.

New Steel Surfaces: Power tool cleaning to St2-St3 according to ISO 8501-1. Surface blasting to near white metal surface cleanliness according to SSPC-SP10 or ISO 8501-1 Sa ½ will improve performance. Depending on ambient conditions, power tool cleaned or blasted surfaces must be primed in maximum 5 hours with **15550 KANEPOX MASTICOAT**.

Previously Painted Surfaces: If the aged coating is in a good condition, it is slightly sanded and cleaned by pressurized fresh water cleaning to remove the dust and other contaminations. Otherwise remove all the cracked and peeling paint by using hand tools to a cleanliness of St 2–St 3 according to ISO 8501-1. If applicable blast cleaning to Sa 2-Sa 2½ according to ISO 8501-1 level to get better results. Water jetting to a minimum degree of Wa 2 ½ (ISO 8501-4:2006) is also applicable as an alternative to abrasive blasting.

A flash rust degree of maximum M (ISO8501-4:2006) is acceptable before application.

Primed/Midcoated Surfaces: Be sure that overcoating period is not exceeded. Otherwise the surfaces must be blasted to have a surface profile.

The Surfaces Other Than Steel: Contact KANAT Project Group for the galvanized, aluminium, plastic surfaces.

Touch-up: Remove all dust, dirt and other foreign material and keep dry. Clean the surface to St2-St 3 level mechanically according to ISO 8501-1 and complete the touch-up application as soon as possible. **15550 KANEPOX MASTICOAT** can be safely used for

APPLICATION PROCEDURES (Mixing Procedure)

This is a two-component paint. Do not mix more material than you plan to use within the listed pot life. Complete containers must be mixed at one time. **DO NOT MIX PARTIAL QUANTITIES FROM CONTAINERS OR PROPER COMPONENT RATIOS MAY NOT BE OBTAINED.**

Prior to mixing, components A Base and B Hardener should be at room temperature (60-75° F/16-24°C). Combine 4 parts by volume of Part B Hardener with 16 parts by volume of Part A Base. Homogenize the mixture with a power mixer, add thinner if necessary before use. Mixed product must be used within 1,5 hours (20°C). 0620 coded thinner should be used for blasted new steels, and 0625 coded thinner should be used for maintenance projects and projects that require surface tolerance.

0620 coded thinner should be used for blasted new steels, and 0625 coded thinner should be used for maintenance projects and projects that require surface tolerance.

MIXING RATIO

Base 15550 : Curing Agent 0363
4 : 1 by volume

APPLICATION CONDITIONS

For the best results;
Temperature must be more than 0°C during the application and/or the curing process.

Surface Temperature: At least 3°C above dew point.
Relative Humidity: 85% maximum.

Good ventilation is required during application.

APPLICATION

Stripe coat all crevices, welds and sharp angles. Apply paint at the recommended film thickness and spreading rate. Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance. Maximum coating interval is 30 days.

Do not apply more than 500 microns WFT to prevent sagging. When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas and pinholes. If necessary, cross spray at a right angle.

15550 KANEPOX MASTICOAT

CLEAN UP

**KANAT THINNER 0644, KANAT THINNER 0625
KANAT THINNER 0620**

APPLICATION EQUIPMENT

(The table is a guide for 20°C)

Application Equipment	Airless Spray	Roller
Thinner maximum	10%	%15
Pressure minimum (bar)	200	-
Nozzle(inch)	0,017-0,023	-

PRECAUTIONS

- Recoating period is minimum 8-10 hours and maximum 1 month (20°C). Recoating interval depends on temperature, humidity and film thickness. If maximum recoating time is exceeded abrade surface, if the surface is highly contaminated apply pressurized fresh water cleaning before recoating.
- Condensation forming on the coating during early times of curing may result in longer cure times, solvent entrapment, premature failure, discoloration or a surface haze or blush that must be removed before recoating.
- High temperatures decrease resistance properties of epoxy based products. Epoxy based products also have a tendency to yellowing, chalking and have limited gloss retention on exterior surfaces.
- Use only **KANAT THINNER 0625** for thinning paint to be applied on previously painted surfaces.

Disclaimer:This product is for professional users only. In case of non-compliance with the instructions or conditions set forth in this document and other additional documents regarding the application of the product, Kanat Paints & Coatings does not accept any responsibility for any damage including but not limited to performance issues. Kanat Paints & Coatings owns all trademarks, patents and licenses mentioned in this document. All values and ratios stated are given in accordance with other values and ratios in the document. All information regarding the product is correct and appropriate to the best of Kanat Paints & Coatings' knowledge, but the factors that are not related to production process, especially external factors, and that may affect the application or use are beyond the control of Kanat Paints & Coatings. It is the user's responsibility to check the validity of this document before using the product. Technical data and instructions published by Kanat Paints & Coatings may change without prior notice. Please contact Kanat Paints for current versions or additional technical data and instructions.