

## 37860 KANPOLY ACR TOPCOAT WT

### PRODUCT DESCRIPTION

**37860 KANPOLY ACR TOPCOAT WT** is an acrylic polyurethane resin based, two component, zinc phosphate containing, high solids, gloss top coat. Can be applied directly to the metal surface in C3 medium corrosive environments. Excellent adhesion and elasticity, color and gloss retention are the characteristic properties. It is resistant to broad range of corrosive and marine atmospheres. Can be applied in thick coats with low dry spray risk.

### RECOMMENDED USE

It has been specially developed for wind energy sector. It can be used as a topcoat acrylic paint in the following structures where high color and gloss resistance is required, for the open atmosphere and exposure to sunlight (UV);

- Wind energy industry
- Structural steels
- Storage tanks and pipes exterior
- Marine structures
- Industrial and port facilities
- Refineries and chemical plants

It provides protection up to C3 corrosion category when used as one coat; up to C4 corrosion category, when applied with a shop primer according to ISO 12944-5 Standard.

It can also be used as a topcoat in paint systems required for C2 to C5 and CX corrosion categories, when applied with a suitable primer and midcoat according to ISO 12944-5 and 12944-9 Standards.

### PRODUCT CHARACTERISTICS

<b>Finish:</b> Gloss/Semi Gloss / Matte	<b>Density (g/ml)</b> 1,62±0,10
<b>Colour:</b> Wide range of colours available	<b>Spreading Rate (m<sup>2</sup>/l)</b> 11,67 (60 microns DFT)
<b>Thinner:</b> Kanat Thinner 0610 (Low Temp.) Kanat Thinner 0615 (High Temp.)	<b>Flash Point</b> 39°C
<b>Mixing Ratio (By Volume)</b> 16 parts A comp. + 2 parts B comp.	<b>VOC ( Volatile Organic Content)</b> 270 gr/l
<b>Mixed Product; Volume Solids (%)</b> 70±2	<b>Application Methods</b> Airless Spray, Conventional Spray, Roller
	<b>Pot Life (20°C)</b> 1,5 hours

### DRYING SCHEDULE(\*)

(60 microns/2 mils film thickness)

	Dry to Touch	Hard Dry	Dry to Over Coat Minimum
5°C	16 hours	24 hours	24 hours
15°C	6 hours	14 hours	14 hours
25°C	3,5 hours	6 hours	7 hours
35°C	2 hours	3 hours	4 hours

Drying values are valid for defined dry film thickness and below 80% relative humidity.

Fully Cured: 7 days (20°C)

(\*) Drying time depends on temperature, humidity and film thickness.

### PACKAGING

One kit of **37860 KANPOLY ACR TOPCOAT WT** is 18 lt.

One pail of **37860 KANPOLY ACR TOPCOAT WT** component A is 16 lt,

One can of **KANPOLY HARDENER 0157** component B is 2 lt.

### SHELF LIFE

Part A–12 months, Part B–12 months when the material is stored in a cool and dry place in unopened original containers.

### HEALTH/SAFETY PRECAUTIONS

Refer to the MSDS sheet prepared according to EU directives before use.

## 37860 KANPOLY ACR TOPCOAT WT

### SURFACE PREPARATION

Surfaces must be dry, clean, free of oil, grease and other foreign material.

**New Steel Surfaces:** Surfaces should be blasted to near-white metal surface cleanliness according to SSPC-SP10 or ISO 8501-1 Sa 2½. Surface cleanliness of St 2-St 3 according to ISO 8501-1 is sometimes allowed depending upon the conditions. Depending on ambient conditions, blasted surfaces must be primed in maximum 5 hours with **37860 KANPOLY ACR TOPCOAT WT**.

**Primed/Midcoated Surfaces:** Follow the overcoating times for primer and/or midcoat, if maximum recoat time is exceeded, abrade surface before top coating. The surfaces must be clean and dust free. Remove all the dust, dirt and other foreign material accumulated during the production and storage by pressurized fresh water cleaning. Topcoat is then applied to completely dry surface.

**The Surfaces Other Than Steel:** Contact to KANAT PAINTS & COATING Project Group for the galvanized, aluminium, plastic surfaces.

**Touch Up:** Contact to KANAT PAINTS & COATING Project Group.

### APPLICATION PROCEDURES (Mixing Procedure)

This is a two-component paint. Do not mix more material than you plan to use within the listed pot life. Complete containers must be mixed at one time.

**DO NOT MIX PARTIAL QUANTITIES FROM CONTAINERS OR PROPER COMPONENT RATIOS MAY NOT BE OBTAINED.**

Prior to mixing, components A Base and B Hardener should be at room temperature (60-75° F/16-24°C). Combine 2 parts by volume of Part B Hardener with 16 parts by volume of Part A Base. Homogenize the mixture with a power mixer, add thinner if necessary before use. Mixed product must be used within 1.5 hours (20°C).

### MIXING RATIO

Base 37860 : Curing Agent 0157  
8:1 by volume

### APPLICATION CONDITIONS

For the best results;

Temperature must be more than 0°C during the application and/or the curing process.

**Surface Temperature:** At least 3°C above dew point.  
**Relative Humidity:** 80% maximum

Good ventilation is required during application.

### APPLICATION

Stripe coat all crevices, welds, and sharp angles. Especially for direct to metal applications. Apply paint at the recommended film thickness and spreading rate. Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance. Maximum coating interval is 6-7 days.

Do not apply more than 200 microns (8 mils) WFT to prevent sagging. When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.

### CLEAN UP

**KANAT THINNER 0644, KANAT THINNER 0610,  
KANAT THINNER 0615**

## 37860 KANPOLY ACR TOPCOAT WT

## APPLICATION EQUIPMENT

(The table is a guide for 20°C)

Application Equipment	Airless Spray	Conventional Spray	Roller
Thinner maximum	%15	%25	%10
Pressure minimum (bar)	150	2,5	—
Nozzle(inch)	0,009-0,015	1,4-1,6	—

## PRECAUTIONS

- Recoating period is minimum 5-6 hours and maximum 6-7 days (20°C). Recoating interval depends on temperature, humidity and film thickness. If maximum recoating time is exceeded abrade surface, if the surface is highly contaminated apply pressurized fresh water cleaning before recoating.
- When using spray application, first apply a mist coat, then full coat after 5-15 minutes by 50% overlap with each pass of the gun to avoid holidays, bare areas and pinholes.
- Do not apply heavy coats beyond the specification otherwise solvent popping may occur.
- B component (**KANPOLY HARDENER 0157**) is sensitive to moisture. Always keep it closed in a dry place. Open carefully because pressure may develop in hot climates. Mixed coating is sensitive to water.
- High humidity and/or dew which is occurred during application or in 12 hours (20°C) after application, can affect film formation negatively, weak adhesion, reduce pot life, softening of the film and loss of gloss can be observed.
- For direct to metal applications; before application of hard to reach areas, lining with a roller or brush shall be made.

**Disclaimer:** This product is for professional users only. In case of non-compliance with the instructions or conditions set forth in this document and other additional documents regarding the application of the product, Kanat Paints & Coatings does not accept any responsibility for any damage including but not limited to performance issues. Kanat Paints & Coatings owns all trademarks, patents and licenses mentioned in this document. All values and ratios stated are given in accordance with other values and ratios in the document. All information regarding the product is correct and appropriate to the best of Kanat Paints & Coatings' knowledge, but the factors that are not related to production process, especially external factors, and that may affect the application or use are beyond the control of Kanat Paints & Coatings. It is the user's responsibility to check the validity of this document before using the product. Technical data and instructions published by Kanat Paints & Coatings may change without prior notice. Please contact Kanat Paints for current versions or additional technical data and instructions.